PRODUCT: JF55610 LA30 K2500

Resin Type: PC/GF10%



| PROPERTIES PROPERTIES | TEST METHOD | CONDITION | UNIT | VALUE |
|-------------------------------|----------------|---------------------------------|---------------------|--|
| CHARACTERISTICS | | | | Glass fiber reinforced Polycarbonate (Non-FR) |
| PHYSICAL | | | | , , |
| Specific Gravity | ASTM D792 | - | - | 1.28 |
| MECHANICAL | | | | |
| Tensile Strength at yield | ASTM D638 | 5mm/min | kgf/cm ² | 620 |
| Tensile Elongation at break | ASTM D638 | 5mm/min | % | 10 |
| Flexural Strength at yield | ASTM D790 | 2.8mm/min | kgf/cm ² | 900 |
| Flexural Modulus | ASTM D790 | 2.8mm/min | kgf/cm ² | 34,000 |
| Izod Impact Strength, notched | ASTM D256 | 1/8 inch at 23 ℃ | kgf·cm/cm | 8 |
| Rockwell Hardness | ASTM D785 | R scale | - | 118 |
| THERMAL | | | | |
| Melt Index | ASTM D1238 | 250℃/10kg | g/10min | 30 |
| HDT | ASTM D648 | 18.6kgf/cm ² , 6.4mm | ${\mathbb C}$ | 130 |
| OTHERS | | | | |
| Flammability | UL94 | - | mm | - |
| Mold Shrinkage | ASTM D955 | Flow at 3.2mm | % | 0.4~0.6 |
| | | | | |

^{1.} The value above is the representative value of the NP or representative color and may have deviation. It can only be used for selecting materials.

^{2.} The value above shall not be regarded as a material specification and cannot be used for molding designs.